Dhr. Geert De Clercq S-PRINT NV Industriezone 5 De Tonne 93 9800 DEINZE

#### via certification

**your visit of** 2008-11-04

your reference

 $our\ reference$ 

late

PVH/10987

Zwijnaarde, 2008-12-02

# **Analysis Report 65716**

Required tests:

Classification of reaction to fire in accordance with ₹N 13501-1:2007

|                | A                               | $\sim 1 11$            |                 |
|----------------|---------------------------------|------------------------|-----------------|
| Identification | Information given by the client |                        | Date of receipt |
| number         |                                 |                        |                 |
| T810580        | quality                         | FP 600                 | 2008-11-04      |
|                | FR treated (\ \ \)              | yes                    |                 |
|                | use-surface                     | 100% polyamide 6       |                 |
|                | substrate, support              | 75% PES – 25% PA       |                 |
|                | backing layer                   | latex                  |                 |
|                | total mass                      | $1,650 \text{ kg/m}^2$ |                 |
|                | pile thickness                  | ±5 mm                  |                 |
|                | total thickness                 | ±6 mm                  |                 |
|                | surface structure               | cut pile               |                 |

Pros Van Hoeyland order responsible

This report runs to 5 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.



| our reference | date       | page |
|---------------|------------|------|
| PVH/10987     | 2008-12-02 | 2/5  |

**Reference:** T810580 - FP 600

#### Classification of reaction to fire in accordance with EN 13501-1:2007

Classification of textile floor coverings in accordance with EN 14041 (2004) § 4.1.4 "The textile floor coverings listed in Table 2, in the end uses identified in the table, are classified without further testing (CWFT) in the classes shown and do not require testing in respect of these end uses and classes".

Table 2 – Classes of reaction to fire for textile floor coverings, classified without further testing

| Floor covering type <sup>1</sup>  | EN product standard | Class <sup>3</sup> Floorings |
|---|---------------------|------------------------------|
| Non-FR machine-made wall-to-wall carpets and pile carpet tiles <sup>2</sup> | EN 1307             | $E_{\mathrm{fl}}$            |
| Non-FR needled textile floor coverings without pile?                        | EN 1470             | $E_{\mathrm{fl}}$            |
| Non-FR needled textile floor coverings with pile                            | EN 13297            | $E_{fl}$                     |

Floor covering glued or loose laid over a Class A2-s1,d0 substrate

- a surface of 100% wool
- a surface of 80% wool or more 20% polyamide or less
- a surface of 80% wool or more 20% polyamide/polyester or less
- a surface of 100% polyamide
- a surface of 100% polypropylene and if with SBR-foam backing, a total mass of > 0.780 kg/m². All polypropylene carpets with other foam backings are excluded.
- Class as provided for in Table 2 in the Annex to Decision 2000/147/EC.

Classification: E<sub>fl</sub>

Textile floor coverings having a total mass of max. 4.8 kg/m², a minimum pile thickness of 1,8 mm (ISO 1766) and

#### **Analysis Report 65716**

our reference date page PVH/10987 2008-12-02 3/5

**Reference:** T810580 - FP 600

#### Classification of reaction to fire in accordance with EN 13501-1:2007

#### 1. Method:

Test Method - EN ISO 9239-1:2002

Standard - EN 13501-1:2007

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Floor covering

- substrate - fibre cement board

- adhesive

- density (1800 ± 200) kg/m<sup>3</sup>
- dimensions 105 cm x 23 cm x 0,5 cm.

: - none / specimens were tested loose laid
: - textile floor coverings are subjected to the laboratory spray extraction - cleaning

cleaning procedure according to ISO 11379

Conditioning

minimum 14 days at  $(23 \pm 2)$  °C and  $(50 \pm 5)$  % RH

until constant mass is achieved

 our reference
 date
 page

 PVH/10987
 2008-12-02
 4 / 5

**Reference:** T810580 - FP 600

2. Results:

End of tests: 1 December 2008

## Radiant heat flux

| Test    | flame s | pread distar | nce (cm)                       | flame time                            | heat flux * kW/m² |
|---------|---------|--------------|--------------------------------|---------------------------------------|-------------------|
|         | 10 min  | 20 min       | 30 min                         |                                       |                   |
| length  |         |              |                                |                                       |                   |
| 1       | 21      | 28           | 28                             | 19 min 55 s                           | 8.0               |
| width   |         |              |                                |                                       |                   |
| 1       | 21      | 31           | 33                             | 26 min 0 s                            | 6.9               |
| 2       | 14      | 14           | 14                             | $\land$ 12 min 0 s                    | 11.0              |
| 3       | 20      | 23           | 23 <                           | $\sqrt{14 \text{ min } 20 \text{ s}}$ | 9.1               |
| average |         |              | </td <td>) )</td> <td>9.0</td> | ) )                                   | 9.0               |

<sup>\*</sup> heat flux at the time of flame extinguishment or after a test duration of 30 minutes.

| Fire classification in accordance with EN 13501-1:2007 |                        |   |  |  |
|--|------------------------|---|--|--|
| Class  | EN ISO 11925-2 or CWFT | EN ISO 9239-1<br>(test duration = 30 min) |  |  |
| $\mathrm{B}_{\mathrm{fl}}$                             | $E_{\mathrm{fl}}$      | heat flux $\geq 8.0 \text{ kW/m}^2$       |  |  |
| ${ m C_{fl}}$  | E <sub>fl</sub>        | heat flux $\geq 4.5 \text{ kW/m}^2$       |  |  |
| $ m D_{fl}$  | ${ m E_{fl}}$          | heat flux $\geq$ 3,0 kW/m <sup>2</sup>    |  |  |

## **Smoke production**

| Test    | maximum light attenuation (%) | total light attenuation<br>(%min) |
|---------|-------------------------------|-----------------------------------|
| length  |                               |                                   |
| 1       | 44                            | 196                               |
| width   |                               |                                   |
| 1       | 50                            | 170                               |
| 2       | 17                            | 36                                |
| 3       | 33                            | 97                                |
| average |                               | 101                               |

| Additional classification in accordance with EN 13501-1:2007 |    |  |
|--|----|--|
| smoke production ≤ 750%.min                                  | s1 |  |
| smoke production > 750%.min                                  | s2 |  |

| our reference | date       | page  |
|---------------|------------|-------|
| PVH/10987     | 2008-12-02 | 5 / 5 |

**Reference:** T810580 - FP 600

### 3. Classification:

Reaction to fire classification:  $B_{fl} / s1$ 

#### Limitations

This classification document does not represent type approval or certification of the product.

\_